



## TECHNICAL DATA SHEET

### PRODUCT

Date: 06/03/15

### PROCOL CERAM

Page 1 to 1

Version 2

#### 1. PRODUCT DESCRIPTION

PROCOL CERAM is a photopolymer emulsion of high viscosity. Solids content: 45%. Blue (sensitized green colour).

Shelf life: 2 years at 20°C in a dark room (diaz's shelf life: 1 year). Sensitized: 3 months at 20°C in a dark room.

#### 2. PRINTING APPLICATION

Resisting to all kinds of inks (water based inks, uv inks, uv water inks, solvents) including aggressive pastes. It is very flexible and it resists to high pressure of the squeegee edges. One of the top range of emulsions, recommended for any work requiring a very high resolution and a very good mechanical resistance.

#### 3. SENSITIZING

Prepare the sensitizer by half filling the bottle with water. Dissolve the powder by shaking the bottle for at least one minute. Mix the sensitizer into the emulsion with a non-metallic instrument. Leave the sensitized emulsion to stand at least one hour to eliminate air bubbles.

##### EXPOSURE TIME:

A preliminary test can be done using the following guidelines:

Use of a 3000 W lamp at 90 cm, 1 coat + 1 coat

Mesh:	Time (seconds):	Mesh:	Time (seconds):
54 T White	62	120 T white	48
90 T White	50	140 T white	45

#### 4. FIRST AID PROCEDURES

##### INHALATION:

None.

##### EYE CONTACT:

Rinse immediately with plenty of water, also under the eyelids, for at least 15 minutes.

In the event of persistent irritation or any lesions, consult an oculist.

##### SKIN CONTACT:

Wash off with soap and water.

##### INGESTION:

Clean mouth with water. Do not induce vomiting.

#### 5. SUPPLIED IN

0.9 KG



4.5 KG

